

**Gasket Constants acc. ASTM F3149-15 / ASME Code**

Gasket material	thickness [mm]	m	y [psi]	y [N/mm <sup>2</sup> ]
<b>novatec<sup>®</sup> PREMIUM XP</b>	1.0	2.8	1450	10
	2.0	2.8	1595	11
	3.0	2.8	1885	13
<b>novatec<sup>®</sup> PLUS</b>	1.0	2.8	3480	24
	2.0	2.8	3770	26
	3.0	2.8	4205	29
<b>novatec<sup>®</sup> SPECIAL</b>	1.0	2.8	4930	34
	2.0	2.8	5220	36
	3.0	2.8	5655	39
<b>novatec<sup>®</sup> 825</b>	1.0	2.8	4930	34
	2.0	2.8	5220	36
	3.0	2.8	5655	39
<b>novatec<sup>®</sup> 925</b>	1.0	2.8	3480	24
	2.0	2.8	3770	26
	3.0	2.8	4205	29

All previous data cease to apply. You may take all current versions from the website [www.frenzelit.com](http://www.frenzelit.com) or ask at Frenzelit directly. The values have been determined with standard laboratory equipment. In view of the variety of different installation and operation conditions and process engineering options, there is no basis for warranty claims referring to the behaviour of the sealing joint. Subject to technical changes and printing errors.

ver. 19-03