

Company Address	Frenzelt GmbH; Frankenhammer; 95460 Bad Berneck	According to DIN EN 13555 2014-07
Gasket Type	novafon® 500	
Sealing element dimensions [mm]	92x49x2.0	

L [mg/(s·m)]	Q _{min/L} [MPa]	Minimum stress to seal Q _{min/L} (at assembly), Q _{Smin/L} (after off-loading) for p = 40 bar				Q _{Smin/L} [MPa]					
		Q _A = 20 MPa	Q _A = 40 MPa	Q _A = 60 MPa	Q _A = 80 MPa						
10 ⁻⁰	12	10	10	10	10						
10 ⁻¹	20	15	10	10	10						
10 ⁻²	26		10	10	10						
10 ⁻³	32		10	10	10						
10 ⁻⁴	39		10	10	10						
10 ⁻⁵	59			55	13						
10 ⁻⁶											
10 ⁻⁷											
10 ⁻⁸											



